

**LISTING OF CLAIMS**

1. (currently amended) A nanodiamond ~~tool~~ article, comprising a mass of sintered nanodiamond particles, said mass consisting essentially of carbon, said mass containing greater than about 95% by volume nanodiamond, and wherein greater than about 98% by volume of said mass is carbon and greater than about 95% by volume of said mass is in the form of nanodiamond, and is substantially free of non-carbon constituents.
2. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond particles are self-sintered.
3. (currently amended) The nanodiamond ~~tool~~ article of claim 1, said mass further comprising in situ grown nanocrystalline diamond.
4. (currently amended) The nanodiamond ~~tool~~ article of claim 3, wherein the in situ grown nanocrystalline diamond is grown from a fullerene carbon source.
5. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said mass consists of carbon.
6. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein the nanodiamond particles have an average diameter of from about 1 nm to about 500  $\mu\text{m}$ .
7. (currently amended) The nanodiamond ~~tool~~ article of claim 6, wherein the nanodiamond particles have an average diameter of from about 1 nm to about 100 nm.
8. (currently amended) The nanodiamond ~~tool~~ article of claim 7, wherein the nanodiamond particles have an average diameter of from about 2 nm to about 30 nm.

9. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein the nanodiamond particles have an average crystal size of from about 1 nm to about 20 nm.
10. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein the nanodiamond particles are randomly oriented.
11. (currently amended) The nanodiamond ~~tool~~ article of claim 1, further comprising a substrate attached to the mass of sintered nanodiamond particles.
12. (currently amended) The nanodiamond ~~tool~~ article of claim 11, wherein the substrate comprises a layer of at least micron-sized diamond particles bonded together by a metal binder, and a support layer bonded to the layer of at least micron-sized diamond particles.
13. (currently amended) The nanodiamond ~~tool~~ article of claim 12, wherein the at least micron-sized diamond particles have an average particle size of from about 0.1  $\mu\text{m}$  to about 100  $\mu\text{m}$ .
14. (currently amended) The nanodiamond ~~tool~~ article of claim 12, wherein the metal binder comprises a member selected from the group consisting of nickel, iron, cobalt, manganese, and mixtures or alloys thereof.
15. (currently amended) The nanodiamond ~~tool~~ article of claim 11, wherein the substrate comprises a member selected from the group consisting of tungsten, titanium, cemented tungsten carbide, cermets, ceramics, and composites or alloys thereof.
16. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond ~~tool~~ article is stable at temperatures up to from about 700 °C to about 1,000 °C.

17. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond ~~tool~~ article is a member selected from the group consisting of cutting tools, drill bits, and wire drawing dies.
18. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond ~~tool~~ article is a heat spreader.
19. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond ~~tool~~ article is a surface acoustic wave filter.
20. (currently amended) The nanodiamond ~~tool~~ article of claim 1, wherein said nanodiamond ~~tool~~ article is a radiation window.
21. (withdrawn) A method of forming a nanodiamond tool, comprising steps of:
- (a) assembling a mass of nanodiamond particles; and
  - (b) sintering the mass of nanodiamond particles to form a sintered mass, said sintered mass containing greater than about 95% by volume nanodiamond particles and greater than about 98% by volume carbon.
22. (withdrawn) The method of claim 21, wherein said mass of nanodiamond particles consists essentially of nanodiamond particles up to the step of sintering, such that the sintered mass is self-sintered.
23. (withdrawn) The method of claim 21, wherein the step of assembling a mass of nanodiamond particles further comprises mixing a fullerene carbon source with the nanodiamond particles.

24. (withdrawn) The method of claim 21, wherein said sintered mass contains greater than about 99% by volume nanodiamond particles.
25. (withdrawn) The method of claim 21, wherein said sintered mass consists of carbon.
26. (withdrawn) The method of claim 21, further comprising the step of disposing a first layer of at least micron-sized diamond adjacent the mass of nanodiamond particles prior to sintering.
27. (withdrawn) The method of claim 26, wherein the layer of at least micron-sized diamond further comprises a metal binder.
28. (withdrawn) The method of claim 27, wherein the metal binder comprises a member selected from the group consisting of nickel, iron, cobalt, manganese, and mixtures and allows thereof.
29. (withdrawn) The method of claim 26, further comprising the step of including a first support material adjacent to the layer of at least micron-sized diamond prior to the step of sintering.
30. (withdrawn) The method of claim 29, wherein the first support material comprises a member selected from the group consisting of tungsten, titanium, cemented tungsten carbide, cermets, ceramics, and composites of alloys thereof.